



**Test Report**

No.T32020290193SN

Date: Sep 21, 2020

Page 1 of 2

BEECARE INTERNATIONAL COMPANY LIMITED  
ROOM C, 6/F., GLORY INDUSTRIAL BUILDING, 22 LEE CHUNG ROAD, CHAI WAN, HONG KONG

The following samples were submitted and identified by/on behalf of the client as:

DISPOSABLE EARLOOP FACE MASK

Case No. : CA320202908129  
 Lot No. / Batch Code : NOT PROVIDED  
 Sample Description : WHITE MASK  
 Quantity Submitted : 18 PCS  
 Sample Receiving Date : SEP 07, 2020  
 Testing Period : SEP 07, 2020 - SEP 21, 2020

Test Requested	Conclusion
Differential pressure (EN14683:2019+AC:2019 Appendix C)	See Result


\*\*\*\*\* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) \*\*\*\*\*

Signed for and on behalf of  
SGS Hong Kong Ltd.

Au Kam Chi, Gigi  
Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



# Test Report

No.T32020290193SN

Date: Sep 21, 2020

Page 2 of 2


## Test Results:

### Differential pressure EN14683:2019+AC:2019 Appendix C

Test Side : Side without strips (Inside)  
 Pre-Conditioning : Minimum of 4 hours at 21±5°C and 85±5% R.H.  
 Test Area : 4.9 cm<sup>2</sup>  
 Flow Rate : 8 l/min

Test Location	ΔP (mm H <sub>2</sub> O/cm <sup>2</sup> )				
	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Top Centre	3.9	4.3	4.6	4.3	4.4
Centre	4.2	4.2	3.9	4.6	4.1
Bottom Centre	3.5	4.3	3.9	4.1	4.3
Centre Left	4.0	4.8	4.4	3.9	3.9
Centre Right	3.7	4.3	4.7	4.6	4.2
Average	3.9	4.4	4.3	4.3	4.2

## Sample Photo:



SGS authenticate the photo on original report only

\*\*\* End of Report \*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.